

Capstone™ ST-100HS

Repellent

Penetrating Sealer for Porous Surfaces

Technical Information

Description

Capstone™ ST-100HS is a cationic aqueous fluorochemical dispersion that provides a durable, non-film forming, transparent protective barrier against oil and water on porous mineral surfaces. Capstone™ ST-100HS is a repellent used in water-based penetrating sealers for natural stone, unglazed tile, grout, terra cotta, concrete, and brick. Capstone™ ST-100HS provides oil and water repellency, stain resistance, and good stain cleanup. It can also be used in cleaning and protecting product formulations.

Applications and Formulating Information

Capstone™ ST-100HS is used in diluted solutions containing 1.5–2.5% active ingredient (6–10% commercial product) working strength with deionized or tap water. Typical coverage rate is from 3–25 m²/L of diluted solution, depending on the porosity of the mineral substrate (thoroughly wet the surface being treated with the diluted product, and remove excess liquid after 15–30 min). The optimum dilution rate should be determined for each application. If blended, maintain pH below 6. **The product may be applied using a saturated brush, roller, paint pad, mop, or low-pressure garden-type sprayer** in one or two layers (to ensure complete coverage). A biocide should be added to formulations made using Capstone™ ST-100HS to protect the formulation against microbial growth.

Typical Properties

Appearance	Slightly hazy, yellow to greenish liquid
Stability	Stable at normal temperatures Perishable if frozen
pH	3.5–5.0
Active Solids, %	25
Density, g/mL	1.1
Flash Point (Closed Cup), °C (°F)	Does not flash
Shelf Life	2 years

Performance

Capstone™ ST-100HS (diluted to 8% of commercial product in water) was compared to a competitive aqueous-based silicone sealer. Each product was applied to limestone and Saltillo (Mexican clay tile or terra cotta) and allowed to dry for three days. **Corn oil, Italian dressing, ketchup, mustard, grape juice, and coffee were then placed on the treated substrates.** After 24 hr, the tiles were washed with 1% soap solution and allowed to dry. The ratings were totaled for each tile sample. The results below show that Capstone™ ST-100HS outperformed the competitive aqueous-based silicone sealer. Similar results have been achieved on other porous mineral substrates.

Scoring System for Each Stain After Dry	
No Visible Stain	0
Very Slight Stain	1
Light Stain	2
Moderate Stain	3
Heavy Stain/Complete Penetration of Stain into Substrate	4

Scoring System for Water/Oil Repellency



5 Contact angle 100-120° 4 Contact angle 75-90° 3 Contact angle 45-75°
 2 Contact angle 25-45° 1 Contact angle 10-25° 0 Contact angle <10°

Performance Comparison

24 hr Stain Scores of Six Stains		
Treatment	Limestone	Saltillo
Capstone™ ST-100HS	4	5
Silicone (aqueous)	8	13
Untreated	19	21

Cumulative scale from 0 (best) to 24 (worst).
 Lower score = Higher performance

Treatment	Oil Repellency	Water Repellency	Stain Resistance
Capstone™ ST-100HS	Excellent	Excellent	Excellent
Silicone (aqueous)	Poor	Excellent	Poor to Good
Untreated	None	None	Very Poor

Personal Safety, First Aid, Storage and Handling

See Safety Data Sheet (SDS) for use and handling recommendations. Review this information with all personnel handling Capstone™ ST-100HS. Mix well before using. Protect from freezing.

Capstone™ Repellents and Surfactants

- Deliver maximum performance
- Regulatory and stewardship information is available upon request
- Are listed on TSCA inventory

Package Sizes

Tote-2,205 lb (1000 kg), Drum-440 lb (200 kg), Pail-44 lb (20 kg)

For questions regarding technical data, commercial supply, and sampling:

Chemours Advanced Performance Materials

Technical Inquiries

Asia Pacific +86.400.671.6789
 Europe +41.22.719.1537
 Latin America +55.08.0011.0728
 North America +1.866.828.7009

Regional Technical Customer Service Center, Americas

The Chemours Company
 Chemours Discovery Hub
 201 Discovery Boulevard
 Newark, DE 19713 USA
 +1.866.828.7009

For more information, visit www.chemours.com/capstone

CAUTION: Do not use or resell Chemours™ materials in medical applications involving implantation in the human body or contact with internal body fluids or tissues unless agreed to by Seller in a written agreement covering such use. For further information, please contact your Chemours representative. For medical emergencies, spills, or other critical situations, call (866) 595-1473 within the United States. For those outside of the United States, call (302) 773-2000.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.