



# Teflon™ PTFE NXT 85

## Modified Granular Fluoroplastic Resin

## Product Information

### Description

Teflon™ PTFE NXT 85 is a free-flowing, pelletized, chemically modified granular resin (its equivalent fine-cut resin is Teflon™ NXT 75). It provides superior processing characteristics in addition to properties of chemically modified resins. When properly processed, it offers an excellent combination of properties that are characteristic of Teflon™ fluoroplastic resins:

- Chemical inertness
- Exceptional dielectric properties
- Heat resistance
- Toughness and flexibility
- Low coefficient of friction
- Non-stick characteristics
- Negligible water absorption
- Excellent weather resistance

This chemically modified resin offers improved resistance to deformation under load, increased resistance to permeation of chemicals, and higher dielectric breakdown strength. Teflon™ PTFE NXT 85 provides a high degree of weldability for applications where the use of elevated temperature and pressure are limited.

### Typical Applications

Teflon™ PTFE NXT 85 can be converted to parts by isostatic, billet, and sheet molding methods, as well as ram extrusion. It can be used for:

- Valve seats
- Fittings
- Pipe valve and vessel liners
- Seal rings

- Bearing pad
- Electrical insulation

This resin is particularly useful in applications where welding of parts to other fluoropolymers such as PFA or standard PTFE is required, e.g., fluid handling systems.

### Processing

Teflon™ PTFE NXT 85 can be processed by all methods used for conversion of free-flow granular PTFE resins to parts. Traditional billet and sheet molding techniques can be used to produce large shapes. More complex parts can be fabricated by automatic and isostatic molding methods. This resin can also be converted to rods and tubes by ram extrusion. All molding methods, except ram extrusion, produce preforms that must be sintered in ovens. Finished product properties depend on preform pressure and the sintering cycle. The sintering cycle is defined by temperature, time, and the cooling rate. Typical properties are listed in Table 1.

### Food Contact Compliance

Properly processed products (sintered at high temperatures common to the industry) made from Teflon™ PTFE NXT 85 resin can qualify for use in contact with food in compliance with FDA Regulation 21 CFR 177.1550.

### Safety Precautions

Before processing any fluoroplastics, read the Material Safety Data Sheet, available upon request from our Customer Service Group at (844) 773-CHEM/2436 in the U.S. or (302) 773-1000 outside of the U.S. Also read the detailed information in the latest edition of the "Guide to the Safe Handling of Fluoropolymer Resins," published by the Fluoropolymers Division of The Society of the Plastics Industry ([www.fluoropolymers.org](http://www.fluoropolymers.org)) or by PlasticsEurope ([www.plasticseurope.org](http://www.plasticseurope.org)).

## Storage and Handling

Preforming is easiest when the resin is between 21–27 °C (70–80 °F). As temperature declines below this range, the resin will be increasingly difficult to mold without cracks and problems with condensed moisture. Higher temperatures inhibit flow and promote lumping. Storage conditions should be set accordingly.

Cleanliness is a critical requirement for successful use of Teflon™ PTFE NXT 85. The white resin and high sintering

temperatures cause even very small foreign particles to become visible in finished moldings. Keep resin drums closed and clean. Good housekeeping and careful handling are essential.

## Packaging

Teflon™ PTFE NXT 85 is packaged in 45-kg (100-lb) drums. Each drum has a bag liner made of polyethylene resin.

**Table 1. Typical Property Data for Teflon™ PTFE NXT 85 Modified Granular Fluoroplastic Resin\***

Property	Test Method	Unit	Typical Value
Average Bulk Density	ASTM D4894	g/L	700
Average Particle Size	ASTM D4894	µm	550
Standard Specific Gravity	ASTM D4894		2.17
Tensile Strength	ASTM D4894	psi (MPa)	4000 (27.6)
Elongation at Break	ASTM D4894	%	450
Deformation Under Load 14 MPa (2,000 psi), 23 °C (73 °F), 24 hr	D621 Method A	%	3.5

Teflon™ PTFE NXT 85 meets the requirements of ASTM D4894-15, Type III, Grade 2, except Bulk Density and Average Particle Size.

\*Typical properties are not suitable for specification purposes.

## HOW TO USE THE TEFLON™ BRAND NAME WITH YOUR PRODUCT

Teflon™ is a registered trademark of Chemours for its brand of fluoroplastic resins, coatings, films, and dispersions. The Teflon™ brand name is licensed by Chemours in association with approved applications. Without a trademark license, customers may not identify their product with the Teflon™ brand name, as Chemours does not sell such offerings with the Teflon™ trademark. Unlicensed customers may refer to the Chemours product offering with only the Chemours name and product code number descriptor as Chemours sells its product offerings. There are no fair use rights or exhaustion of rights to use the Teflon™ trademark from buying from Chemours, a Chemours customer, or a distributor without a trademark license from Chemours.

If you are interested in applying for a trademark licensing agreement for the Teflon™ brand, please visit [www.teflon.com/license](http://www.teflon.com/license)

**CAUTION:** Do not use or resell Chemours materials in medical applications involving implantation in the human body or contact with internal bodily fluids or tissues unless agreed to by Seller in a written agreement covering such use. For further information, please contact your Chemours representative. For medical emergencies, spills, or other critical situations, call (866) 595-1473 within the United States. For those outside of the United States, call (302) 773-2000.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For more information, visit [teflon.com/industrial](http://teflon.com/industrial)

For sales and technical support contacts, visit [teflon.com/industrialglobalsupport](http://teflon.com/industrialglobalsupport)

© 2020 The Chemours Company FC, LLC. Teflon™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: K-15317

C-10145 (3/20)