

## Technical Information

### Introduction

Viton™ GF-200S\* fluoroelastomer is a 70% fluorine, peroxide-cured fluoroelastomer similar to Viton™ GF-600S, but with a significantly lower gum polymer viscosity of -25 (ML at 121 °C [250 °F]). Viton™ GF-200S utilizes the latest technology from Chemours, advanced polymer architecture (APA), which includes a novel peroxide cure site along with an optimized molecular weight distribution.

### Features

- Excellent fluid resistance to aromatic hydrocarbons and alcohols, including methanol, oils, steam, and acids
- Is ideal for blending with Viton™ GF-600S to reach intermediate viscosity ranges for injection molding
- Improved mold release/mold fouling properties
- Improved mold flow and less shear sensitivity than 65 Mooney Viton™ GF-600S
- Excellent physical properties with high elongation, both original and aged
- Heat, fluids, and low temperature properties comparable to Viton™ GF and GF-600S
- Improved water resistance/lower volume swell in water
- Excellent compression set resistance with either low or no post-cure

### Processing

A load factor of >72% for internal mixing of Viton™ GF-200S is suggested. The suggested process aids for Viton™ GF-200S are 0.75 phr of Struktol® HT-290, either alone or in combination with 0.5 phr of PAT-777, or combinations of 0.5 phr Armeen® 18D with carnauba wax or Struktol® WS-280. The use of TMAIC (trimethylallyl isocyanurate) is NOT suggested, as it causes poor mold release and high compression set. Viton™ Curative No. 7 (VC-7) is the suggested coagent for all Viton™ GF-200S compounds and is usually used at a 2.5 phr level or lower, unless high modulus is needed. High levels of VC-7 can bleed out and cause molding flaws.

### Safety and Handling

Before handling or processing Viton™ GF-200S, be sure to read and be guided by the suggestions in the Chemours technical bulletin, "Handling Precautions for Viton™ and Related Chemicals."

### Product Description

Chemical Composition	Copolymer of hexafluoropropylene, vinylidene fluoride, and tetrafluoroethylene with a cure site monomer
Physical Form	Sheet
Appearance	White to tan
Odor	None
Mooney Viscosity, ML 1 + 10 at 121 °C (250 °F)	25
Specific Gravity	1.90
Storage Stability	Excellent
Fluorine, %	~70

Viton™ GF-200S was formerly named VTR-8605.

**Table 1. General Properties of Viton™ GF-200S Compared to Viton™ GF-300**

	Viton™ GF-300	Viton™ GF-200S	50/50 Blend	Viton™ GF-600S
<b>Mooney Viscosity (ML 1 + 10 at 121 °C [250 °F]) on Gum Polymers</b>				
1 + 10 Reading	30	23	38	58
<b>Compound DD-1964 No.</b>	<b>A48-01</b>	<b>A48-03</b>	<b>A48-04</b>	<b>A48-05</b>
Viton™ GF-300	100	—	—	—
Viton™ GF-200S	—	100	50	—
Viton™ GF-600S	—	—	50	100
Zinc Oxide	3	3	3	3
N990 (MT Black)	30	30	30	30
Viton™ Curative No. 7 (VC-7)	3	3	3	3
Varox® DBPH-50	2	2	2	2
Total phr Lab	138	138	138	138
<b>Mooney Scorch at 121 °C (250 °F)</b>				
Minimum, MJ	18	13	22	31
2 Pt. Rise, min	26.5	24.8	23.0	18.4
5 Pt. Rise, min	29.1	26.2	24.2	19.8
10 Pt. Rise, min	>30	27.7	25.7	20.9
<b>ODR at 162 °C (324 °F), 3 Degree Arc, 100 Range, 30 Min Clock</b>				
M-L, dNm	7	6	10	16
ts-2, min	1.4	1.4	1.3	1.4
t'50, min	3.2	3.1	3.0	3.1
t'90, min	6.6	5.8	5.3	6.2
M-H, dNm	136	173	168	166
<b>MDR 2000 at 177 °C (351 °F), 0.5 Degree Arc, 100 Range, 12 Min Clock</b>				
M-L, dNm	0.7	0.6	1.1	1.7
ts-2, min	0.5	0.4	0.4	0.4
t'50, min	0.7	0.7	0.7	0.6
t'90, min	1.6	1.1	1.1	1.0
t'95, min	2.2	1.4	1.3	1.3
M-H, dNm	23.6	33.6	33.2	32.7
<b>Physical Properties at RT—Original (Cured 7 min at 177 °C [351 °F]—No Post-Cure)</b>				
M-100, MPa	3.6	4.5	4.8	4.7
Tensile, MPa	12.3	13.3	13.3	14.3
T-B, psi	1,781	1,930	1,931	2,069
Elongation, %	336	278	264	291
Hardness A, pts	69	71	70	71
<b>“Hot” Tear Strength at 150 °C (302 °F)—Original (Cured 7 min at 177 °C [351 °F]—No Post-Cure)</b>				
Tear Die B, N/mm	11.2	11.4	10.5	10.9
<b>Physical Properties at RT—Original (Cured 7 min at 177 °C [351 °F]—Post-Cured 2 hr at 232 °C [450 °F])</b>				
M-100, MPa	5.0	6.3	6.6	6.2
Tensile, MPa	20.0	18.0	18.7	20.0
T-B, psi	2,904	2,614	2,714	2,904
Elongation, %	300	246	237	285
Hardness A, pts	72	76	74	74

continued

**Table 1. General Properties of Viton™ GF-200S Compared to Viton™ GF-300 (continued)**

	Viton™ GF-300	Viton™ GF-200S	50/50 Blend	Viton™ GF-600S
<b>Compression Set , Method B, O-Rings</b>				
22 hr at 200 °C (392 °F)				
– No Post-Cure	34	20	20	19
– Post-Cure at 232 °C (450 °F)	26	16	14	16
70 hr at 200 °C (392 °F)				
– No Post-Cure	43	26	24	24
– Post-Cure at 232 °C (450 °F)	36	20	19	20
<b>Physical Properties at RT—Heat-Aged 70 hr at 250 °C (482 °F) in Oven</b>				
M-100, MPa	4.9	5.2	5.6	5.4
% Change, M-100	–1	–17	–15	–13
Tensile, MPa	17.0	18.6	18.2	18.2
% Change, T-B	–15	3	–3	–9
Elongation, %	325	296	275	293
% Change, E-B	8	20	16	3
Hardness, A, pts	75	78	77	77
Pts Change	3	2	3	3
<b>Physical Properties at RT—Heat-Aged 70 hr at 275 °C (527 °F) in Oven</b>				
M-100, MPa	3.0	3.8	4.1	4.2
% Change, M100	–40	–40	–39	–33
Tensile, MPa	7.3	11.8	12.9	13.2
% Change, T-B	–64	–34	–31	–34
Elongation, %	391	355	347	340
% Change, E-B	30	44	47	19
Hardness, A, pts	75	78	77	77
Pts Change	3	2	3	3
<b>Physical Properties at RT—Aged 168 hr at 100 °C (212 °F) in ASTM # 105 Oil (5W/30 Motor Oil)</b>				
M-100, MPa	6.2	7.0	6.4	6.7
% Change, M100	23	12	–3	8
Tensile, MPa	10.6	10.8	10.4	10.5
% Change, T-B	–47	–40	–45	–47
Elongation, %	154	141	145	140
% Change, E-B	–49	–43	–39	–51
Hardness, A, pts	75	79	77	77
Pts Change	3	3	3	3
Volume Swell, %	1.4	1.6	1.6	1.6
<b>Low Temperature Testing (Post-Cured)</b>				
T <sub>g</sub> by DSC, °C (Inflection)	–6.1	–5.0	–5.4	–6.0
<b>Fluid Immersions - Volume Swell—168 hr at 23 °C (73 °F), Unless Noted</b>				
Fuel C, %VS	2.5	2.9	3.4	3.3
M1.5 Fuel, %VS	6.3	7.0	7.2	7.7
Methanol, %VS	3.7	3.4	3.3	3.3
Distilled Water at 100 °C (212 °F)	4.9	3.7	3.7	3.8

## Test Procedures

Property Measured	Test Procedure
Compression Set	ASTM D395, Method B (25% deflection)
Hardness	ASTM D1414, durometer A
MDR (moving die rheometer)	ASTM D5289
Mooney Scorch	ASTM D1646, small rotor at 121 °C (250 °F)
Mooney Viscosity	ASTM D1646, ten pass at 121 °C (250 °F)
ODR (oscillating disk rheometer)	ASTM D2084
Property Change After Heat Aging	ASTM D573
Stress/Strain Properties 100% Modulus Tensile Strength (T-B) Elongation (E-B)	ASTM D412, pulled at 8.5 mm/sec (20 in/min)
Tear Die B	ASTM D624
T <sub>g</sub> by DSC	DDE Custom (Akron MDSC – T <sub>g</sub> )
Volume Change in Fluids	ASTM D471

Test temperature is 23 °C (73 °F), except where specified otherwise.

## For more information, visit [Viton.com](http://Viton.com)

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

© 2020 The Chemours Company FC, LLC. Viton™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: VTE-A10164-00-A0705

C-11074 (9/20)