

# Tefzel™ ETFE

## Fluoropolymer Film

## Properties Bulletin

### Description

Tefzel™ ETFE film is a transparent, thermoplastic film that can be heat sealed, thermoformed, vacuum formed, heat bonded, welded, metallized, laminated (combined with dozens of other materials), and used as an excellent hot-melt adhesive. This wide variety of fabrication possibilities combines with the following important properties to offer a unique balance of capabilities not available in other plastic films.

### Chemical Compatibility

Tefzel™ ETFE film is chemically inert and solvent-resistant to virtually all chemicals, except molten alkali metals, gaseous fluorine, and certain complex halogenated compounds, such as chlorine trifluoride, at elevated temperatures and pressures. It also has low permeability to liquids, gases, moisture, and organic vapors.

### Electrical Reliability

- Superior reliability and retention of properties over large areas of film
- High dielectric strength, over 160 kV/mm for 0.025-mm film (4000 V/mil for 1-mil film)
- No electric tracking, non-wettable, and non-charring
- Very low power factor and dielectric constant

### Wide Thermal Range

- Continuous service temperature: -100 to 150 °C (-150 to 300 °F)
- Melting range: 260 to 280 °C (500 to 536 °F)
- Heat sealable

### Mechanical Toughness

- Superior anti-stick and low frictional properties
- High resistance to impact and tearing

### Long Time Weatherability\*

- Inert to outdoor exposure
- High transmittance of ultraviolet and all, but far, infrared

### Reliability

- Tefzel™ ETFE film contains no plasticizers or other foreign materials.
- Conventional equipment and techniques can be used for processing; basic composition and properties will not be influenced.
- Rigid quality control by Chemours ensures uniform gauge, void-free film.

### Tefzel™ ETFE Film

The convenience of Tefzel™ ETFE fluoropolymer in easy-to-use film facilitates the design and fabrication of this low friction thermoplastic for all sorts of high performance jobs. It is transparent and can be heat sealed, thermoformed, welded, and heat bonded. Superior anti-stick properties make it an ideal release film for many applications. A cementable type with an invisible surface treatment is available for bonding to one or both sides with adhesives. This versatility is augmented by the superior properties of a true melt-processible fluoropolymer and the wide choice of product dimensions available from Chemours.

---

\*Type C film is not recommended for outdoor use.

**Table 1: Typical Properties of Tefzel™ ETFE Fluoropolymer Film**

Property	Test Method*	Typical Value**	
		SI Units	English Units
<b>Mechanical</b>			
Tensile Strength at Break	D882	41 MPa	6000 psi
Elongation at Break	D882		300%
Flex Modulus	D882	830 MPa	120,000 psi
Folding Endurance (MIT)	D2176		50,000 cycles
Tear Strength—Initial (Graves)	D1004	4.90 N	500 g
Tear Strength—Propagating (Elmendorf)	D1922	0.74 N	75 g
<b>Thermal</b>			
Melt Point	D3418	260–280 °C	500–536 °F
Thermal Conductivity	Cenco-Fitch	0.24 W/(m·K)	1.65 Btu·in/(hr·ft <sup>2</sup> ·°F)
Specific Heat	—	1172 J/(kg·K)	0.28 Btu/(lb·°F)
Dimensional Stability	30 min at 150 °C (302 °F)		MD = 1% shrinkage TD = 5% shrinkage
Oxygen Index	D2863		30%
<b>Electrical</b>			
Dielectric Strength, short-time, in air at 23 °C (73 °F), 6.35 mm (1/4 in) diameter electrode, 0.79 mm (1/32 in) radius, 60 Hz, 500 V/s rate of rise: 0.025 mm (1 mil) film	D149 Method A	160 kV/mm	4000 V/mil
Dielectric Constant, 25 °C (77 °F), 1 KHz	D150		2.6
Dissipation Factor, 25 °C (77 °F), 1 KHz	D150		0.0007
Volume Resistivity, 170 °C (338 °F)	D257		>1 x 10 <sup>17</sup> ohm·cm
<b>Chemical</b>			
Moisture Absorption	—		<0.02%
Permeability, Gas: Carbon Dioxide Nitrogen Oxygen	D1434		cm <sup>3</sup> /(m <sup>2</sup> ·24 hr·atm)*** 3.9 x 10 <sup>3</sup> 0.5 x 10 <sup>3</sup> 1.6 x 10 <sup>3</sup>
Permeability, Vapor: Water	E96	g/(m <sup>2</sup> ·d) 7.8	g/(100 in <sup>2</sup> ·24 hr) 0.5
<b>General</b>			
Density	D1505	1700 kg/m <sup>3</sup>	106 lb/ft <sup>3</sup>
Coefficient of Friction Kinetic (Film-to-Steel)	D1894		0.2–0.3
Refractive Index	D542		1.4
Solar Transmission	E424		90%

\*ASTM method, unless otherwise specified

\*\*For 0.050-mm (2-mil) film at 25 °C (77 °F), unless otherwise specified

\*\*\*To convert to cm<sup>3</sup>/(100 in<sup>2</sup>·24 hr·atm), multiply by 0.0645

**Table 2: Types and Gauges of Tefzel™ ETFE Fluoropolymer Film**

Gauge	50	100	200	500
Thickness, mil	0.5	1	2	5
Thickness, $\mu\text{m}$	12.5	25	50	125
Approx. area factor, $\text{ft}^2/\text{lb}$	200	100	50	20
Approx. area factor, $\text{m}^2/\text{kg}$	40	20	10	4
<b>Availability</b>				
Type LZ—ETFE, general-purpose	X	X	X	X
Type CLZ—ETFE, one side cementable	—	X	X	X
Type CLZ-20—ETFE, both sides cementable	—	X	X	—

Note: Each roll of Tefzel™ film is clearly identified as to resin type, film thickness, and film type.

<b>ETFE</b>	<b>200</b>	<b>CLZ</b>
Resin type	Film thickness, 200 gauge, 2 mil	Film type, cementable one side

## HOW TO USE THE TEFZEL™ BRAND NAME WITH YOUR PRODUCT

Tefzel™ is a registered trademark of Chemours for its brand of ETFE fluoropolymer resins. The Tefzel™ brand name is licensed by Chemours in association with approved applications. Without a trademark license, customers may not identify their product with the Tefzel™ brand name as Chemours does not sell such offerings with the Tefzel™ trademark. Unlicensed customers may refer to the Chemours product offering with only the Chemours name and product code number descriptor as Chemours sells its product offerings. There are no fair use rights or exhaustion of rights to use the Tefzel™ trademark from buying from Chemours, a Chemours customer or a distributor without a trademark license from Chemours.

If you are interested in applying for a trademark licensing agreement for the Tefzel™ brand, please visit [teflon.com/license](https://teflon.com/license)

**CAUTION:** Do not use or resell Chemours materials in medical applications involving implantation in the human body or contact with internal bodily fluids or tissues unless agreed to by Seller in a written agreement covering such use. For further information, please contact your Chemours representative. For medical emergencies, spills, or other critical situations, call (866) 595-1473 within the United States. For those outside of the United States, call (302) 773-2000.

The information set forth herein is furnished free of charge and based on technical data that Chemours believes to be reliable. It is intended for use by persons having technical skill, at their own discretion and risk. The handling precaution information contained herein is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Because conditions of product use are outside our control, Chemours makes no warranties, express or implied, and assumes no liability in connection with any use of this information. As with any material, evaluation of any compound under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate under or a recommendation to infringe any patents.

NO PART OF THIS MATERIAL MAY BE REPRODUCED, STORED IN A RETRIEVAL SYSTEM OR TRANSMITTED IN ANY FORM OR BY ANY MEANS ELECTRONIC, MECHANICAL, PHOTOCOPYING, RECORDING OR OTHERWISE WITHOUT THE PRIOR WRITTEN PERMISSION OF CHEMOURS.

For more information, visit [teflon.com/tefzel](https://teflon.com/tefzel)

For sales and technical support contacts, visit [teflon.com/industrialglobalsupport](https://teflon.com/industrialglobalsupport)

© 2017 The Chemours Company FC, LLC. Teflon™, Tefzel™ and any associated logos are trademarks or copyrights of The Chemours Company FC, LLC. Chemours™ and the Chemours Logo are trademarks of The Chemours Company.

Replaces: K-26943

C-10201 (9/17)